




Method description
 ASTM 3574-05 Test E Tensile Stress and Elongation
 Sample file name: Line 2 New Process 14mm.is_tens

Specimen 1 to 9



	Specimen label	Maximum Tensile Strength [psi]	Maximum Elongation [%]	Specimen Note
1	Bottom	62.66	20.40	
2	Bottom	72.85	27.52	
3	Bottom	66.88	16.39	
4	Top	65.72	15.14	
5	Top	60.96	17.05	
6	Top	78.30	21.51	
7	Middle	69.99	17.40	
8	Middle	80.88	22.33	
9	Middle	84.19	22.47	
Mean		71.38	20.02	
Standard deviation		8.24	3.92	
Coefficient of variation		11.5	19.6	