




Method description
 ASTM 3574-05 Test E Tensile Stress and Elongation
 Sample file name: Line 2 New Process 17mm.is_tens

Specimen 1 to 9



	Specimen label	Maximum Tensile Strength [psi]	Maximum Elongation [%]	Specimen Note
1	Top	75.70	19.02	
2	Top	69.08	18.07	
3	Top	56.59	18.25	
4	Middle	68.66	19.18	
5	Middle	84.26	20.85	
6	Middle	68.50	14.02	
7	Bottom	62.89	17.85	
8	Bottom	73.89	24.55	
9	Bottom	74.31	20.05	
Mean		70.43	19.09	
Standard deviation		7.93	2.80	
Coefficient of variation		11.3	14.7	