




Method description
 ASTM 3574-05 Test E Tensile Stress and Elongation

Sample file name: PBYSR GEN 3-6.6.2017.is_tens

Specimen 1 to 6



	Specimen label	Maximum Tensile Strength [psi]	Maximum Elongation [%]	Specimen Note
	1	93.56	32.58	Geometry Removed
	2	94.62	45.20	Geometry Removed
	3	91.91	33.58	Geometry Removed
	4	95.58	46.07	Geometry Removed
	5	90.12	46.74	Geometry Removed
	6	87.81	45.25	Geometry Removed
	Mean	92.27	41.57	
	Standard deviation	2.93	6.61	
	Coefficient of variation	3.2	15.9	